



- Designation of fitting.
- Lot number.

Each fitting conforming to this standard shall also be marked with BIS standard mark.

5.0 INSPECTION/ DOCUMENTS

- Inspection shall be carried out as per OWNER Technical Specification.
- OWNER representative or Third Party Inspection Agency appointed by OWNER shall carry out stage wise inspection during manufacturing/final inspection.
- Vendor shall furnish all the material test certificates, proof of approval/ license from specified authority as per specified standard, if relevant, internal test inspection reports as per OWNER Tech Spec. &- specified code for 100% material, at the time of final inspection of each supply lot of material.
- Even after third party inspection, OWNER/ OWNER REPRESENTATIVE reserves the rights to select a sample of fittings randomly from each manufacturing batch & have these independently tested. Should the results of these tests fall outside the limits specified in OWNER technical specification, then OWNER/ OWNER REPRESENTATIVE Reserves the rights to reject all production supplied from the batch. (ASTM D- 2247)

Weathering :60-70% Gloss retention after 1000Hrs.
 (sun test with water immersion, Xenon 150K.lux)

Colour : Light colour as approved by OWNER/CONSULTANT



ENERGISING QUALITY

VCS QUALITY SERVICES PVT. LTD.

STANDARD SPECIFICATION – WARNING MAT

VPC –SS-PE-0013

00	18.06.18	ISSUED AS STANDARD	BS	MVK	AD
REV. No	DATE	Purpose	Prepared By	Checked By	Approved By



CONTENTS

1.0	SCOPE	3
2.0	DEFINATIONS.....	3
3.0	REFERENCE CODE.....	3
4.0	FEATURES	3
5.0	QUALITY ASSURANCE (QA)	4
6.0	DEFECT LIABILITY	4
7.0	APPENDIX - I	4



1.0 SCOPE

INDRAPRASTHA GAS LTD. (IGL) plans to augment the PNG Network. It supplies natural gas to domestic & commercial consumers in the city of NCT Delhi, Uttar Pradesh, Haryana & Rajasthan GA.

The present document covers the technical specifications for the procurement of Warning Mat. Warning mats shall be laid in the ground above the gas main line in order to indicate their presence.

2.0 DEFINATIONS

Owner	Shall mean Indraprastha Gas Ltd. (IGL).
Manufacturer	Means the Manufacturer of the Steel Reinforced Rubber Hose.
SS	Means the present <<Standard Specification>> and its appendix, if any.
Third Party Inspection Agency	Means the Inspection Agency to be appointed by IGL.

3.0 REFERENCE CODE

IS 10889	High Density Polyethylene Films
ASTM D - 638	Standard test method for tensile properties of plastics.

4.0 FEATURES

• Material

Raw material of the warning mat shall be Virgin material.

The material grade of Warning Mat shall be HDPE with warning sticker / stamp.

- Mechanical properties
- Tensile strength at break (Machine direction) - 300 Kgf /cm²(minimum)
- Elongation in machine & Transverse direction (%) - 300 (minimum)

• Colour

The Mat shall be of bright golden yellow colour. This colour must not take any appreciable alteration in the course of time.

• Dimensions

Warning Mat shall have following dimensions:

Width 300 mm ± 5 mm

Thickness 1 mm (Minimum)

Negative tolerance on thickness is not allowed.

• Marking

- Marking on the Mat shall be approved by owner. The warning Mat shall be provided with Chainage marking and the warning mat must be engraved with "Caution: High pressure gas pipeline below" in both English and Hindi along with IGL's Logo at a frequency of every meter.
- Vendor shall submit proposed Artwork to be marked on the Mat for the approval

from Owner / Owner’s representative.

- **Tests**

- a. Colour- Fast test

Test specimen 100 mm to 150 mm wide shall be immersed in a 20% solution of ammonium sulphide at 15 to 20 °C temperature for 15 days. The colour fastness shall be evaluated by comparing the test specimen with a sample specimen. The comparison shall be made by placing the two specimens on a white back ground in day light, but without exposing them directly to sun light. Test shall be accepted satisfactory, if the colour of the strip remains intact.

- b. Other tests shall be carried out as per relevant national / international standard enclosed in QAP.

- **Packing**

The warning mat shall be delivered in rolls of 50meters. Packing size to be mentioned to ensure uniformity in delivery conditions of the materials being procured. Bidder shall submit the packing details during offer and also compiled with at the time of delivery.

5.0 QUALITY ASSURANCE (QA)

Manufacturer shall prepare detailed QAP and submit for the approval from Owner / Owner’s representative.

6.0 DEFECT LIABILITY

Defect liability period shall be as per the commercial volume I of II

7.0 APPENDIX - I

Vendor to submit the following Data along with BID.

SR.NO.	DESCRIPTION	UNIT	DATA	REMARKS
01.	Average gravimetric Thickness	mm		
02.	Tensile strength at Break (in machine direction)	Kg / cm ²		
03.	Tensile strength at Break (in Transverse direction)	Kg / cm ²		
04.	Elongation at Break (in Transverse direction)	%		
05.	Elongation at Break (in Transverse direction)	%		
06.	Color bleeding	-		
07.	Dimensional stability	% change		



**STANDARD SPECIFICATION
FOR
SEAMLESS FITTINGS AND FLANGES {SIZE UPTO DN
400MM(16")}**

TOTAL
SHEETS

07

DOCUMENT NO

SS

PL


025

**STANDARD SPECIFICATION
FOR
SEAMLESS FITTINGS
AND FLANGES {SIZE UPTO DN 400MM(16")}**

0	10.07.2017	ISSUED AS STANDARD SPECIFICATION	BS	MV	AD
REV	DATE	DESCRIPTION	PREP	CHK	APPR

ABBREVIATIONS:

ASME	American Society of Mechanical Engineers
ASTM	American Society for Testing and Materials
API	American Petroleum Institute
BHN	Brinell hardness number
HAZ	Heat Affected Zone
MSS-SP	Manufacturers Standardization Society - Standard Practice
RTJ	Ring Type Joint
SSPC	Steel Structures Painting Council
CE	Carbon Equivalent
LTCS	Low Temperature Carbon Steel
LPG	Liquefied Petroleum Gas

	STANDARD SPECIFICATION FOR SEAMLESS FITTINGS AND FLANGES {SIZE UPTO DN 400MM(16")}	Document No.	Rev
		SS-PL-025	0
		Page 2 of 7	

CONTENTS

1.0 SCOPE 4

2.0 REFERENCE DOCUMENTS 4

3.0 MATERIALS 5

4.0 DESIGN AND MANUFACTURE 5

5.0 INSPECTION AND TESTS 6


6.0 PAINTING 7

7.0 MARKING 7

8.0 TEST CERTIFICATES 7

9.0 PACKING & SHIPPING 7

10.0 DOCUMENTATION 7

	STANDARD SPECIFICATION FOR SEAMLESS FITTINGS AND FLANGES {SIZE UPTO DN 400MM(16")}	Document No.	Rev
		SS-PL-025	0
		Page 3 of 7	

1.0 **SCOPE**

This Technical specification specifies the minimum requirements for the design, manufacture and supply of following carbon steel flanges (such as welding neck flanges, blind flanges, spectacle blinds, spacers and blind etc) and seamless fittings (such as tees, elbows, reducers, caps, outlets etc) size DN up to 400 mm (16”) to be installed in onshore pipeline systems handling non-sour hydrocarbons in liquid or gaseous phase including Liquefied Petroleum Gas (LPG).

2.0 **REFERENCE DOCUMENTS**

Reference has been made in this specification to the latest edition (edition enforce at the time of issue of enquiry unless specified otherwise) of the following Codes, Standards and Specification.

AMERICAN SOCIETY OF MECHANICAL ENGINEERS (ASME)

B31.4	:	Pipeline Transportation system for liquid Hydrocarbon & other liquids.
B 31.8	:	Gas Transmission and Distribution Piping Systems.
B16.5	:	Pipe Flanges and Flanged Fitting.
B16.9	:	Factory made Wrought Butt Weld Fittings.
B 16.11	:	Forged Steel Fittings, Socket welding and Threaded.
B 16.48	:	Steel Line Blanks.
Section VIII	:	Boiler and Pressure Vessel Code - Rules for Construction of Pressure Vessels.
Section IX	:	Welding and Brazing Qualifications.


AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A370	:	Standard Test Methods and Definitions for Mechanical Testing of Steel Products.
------	---	---

MANUFACTURERS STANDARDIZATION SOCIETY (MSS)

SP-25	:	Standard Marking System for Valves, Fittings, Flanges and Unions.
SP-97	:	Forged Carbon Steel Branch Outlet Fittings- Socket Welding, Threaded and Butt Welding Ends

In case of conflict between various requirements of this specification and the requirements

	STANDARD SPECIFICATION FOR SEAMLESS FITTINGS AND FLANGES {SIZE UPTO DN 400MM(16”)}	Document No.	Rev
		SS-PL-025	0
		Page 4 of 7	

of above referred Codes and Standards, more stringent requirement shall apply unless otherwise agreed by Purchaser.

3.0 **MATERIALS**

The Material of flanges & fittings shall be as indicated in purchase requisition. In addition, the material shall also meet the requirements specified hereinafter.

- 3.1 The Carbon Steel used for the manufacture of flanges and fittings shall be fully killed.
- 3.2 The carbon equivalent (CE) shall not exceeding 0.45, based on check analysis calculated in accordance with following.

$$CE = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

- 3.3 For flanges and fittings specified to be used for gas service or LPG service, Charpy V-notch test shall be conducted on each heat of steel. Unless specified otherwise, the Charpy V-notch test shall be conducted at 0° C in accordance with the impact test provisions of ASTM A 370 for flanges and MSS-SP-75 for all fittings.


The average absorbed impact energy values of three full-sized specimens shall be 27 joules. The minimum impact energy value of any one specimen of the three specimens analyzed as above shall not be less than 22 Joules.

When Low Temperature Carbon Steel (LTCS) materials are specified for flanges and fittings in Purchase Requisition, the Charpy V-notch test requirements of applicable material standard shall be complied with.

- 3.4 For flanges and fittings specified to be used for Gas service or LPG service, Hardness test shall be carried out as per ASTM A 370 for each heat of steel used. A full thickness cross section shall be taken for this purpose and the maximum hardness of base metal, Weld metal and heat affected zone shall not exceed 248 HV₁₀.
- 3.5 In case of RTJ (Ring Type Joint) flanges, the groove hardness shall be minimum 140 BHN. Ring Joint flanges shall have octagonal section of Ring joint.

4.0 **DESIGN AND MANUFACTURE**

- 4.1 Flanges such as weld neck flanges and blind flanges shall conform to the requirements of ASME B 16.5.
- 4.2 Spectacle blind and spacer & blind shall conform to the requirements of ASME B 16.48.
- 4.3 Fittings such as tees, elbows, reducers, etc. shall be seamless type and shall conform to ASME B 16.9 for sizes DN 50mm (2") to DN 400mm (16") (both sizes included) and ASME B 16.11 for sizes DN 15mm(1½") & below.
- 4.4 Fittings such as weldolets, sockolets, nippolets, etc. shall be manufactured in accordance with MSS-SP-97.
- 4.5 Repair by Welding on flanges and fitting is not permitted.

	STANDARD SPECIFICATION FOR SEAMLESS FITTINGS AND FLANGES {SIZE UPTO DN 400MM(16")}	Document No.	Rev
		SS-PL-025	0
		Page 5 of 7	